

LOOSE LAY 5052 | 50X50 CM

PRODUCT SPECIFICATIONS

|                      |                       |                                                                                   |           |
|----------------------|-----------------------|-----------------------------------------------------------------------------------|-----------|
| Finishing            | Vellingkanten         |                                                                                   |           |
| Surface structure    | Universal embossed    |                                                                                   |           |
| Total weight         | EN ISO 24340 (EN 429) |  | 9050 g/m² |
| Total thickness      | EN ISO 24346 (EN 428) |  | 5.0 mm    |
| Wear layer thickness | EN ISO 24340 (EN 429) |                                                                                   | 0.55 mm   |
| Design               | Steen                 |                                                                                   |           |

PERFORMANCE SPECIFICATIONS

|                            |                      |                                                                                                                                                                            |           |
|----------------------------|----------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------|
| Dimensional stability      | EN ISO 23999         |                                                                                                                                                                            | ≤ 0.10%   |
| Residual indentation       | EN ISO 24343-1       |                                                                                          | ≤ 0.10 mm |
| Slip resistance            | EN 13893 DIN 51130   |                                                                                         | R9        |
| Light fastness             | DIN EN ISO 105 Bo2   |                                                                                         | ≥ 6       |
| Usage classification       | EN ISO 10874 EN 685  | <br> | 33<br>42  |
| Castor chair test (Type W) | EN ISO 4918 (EN 425) | Geschikt voor bureaustoelen met type W                                                                                                                                     |           |

TECHNICAL SPECIFICATIONS

|                    |              |                                                                                     |              |
|--------------------|--------------|-------------------------------------------------------------------------------------|--------------|
| Flammability       | DIN EN 13501 |  | Bfl-s1       |
| Thermal resistance | EN 12664     |                                                                                     | 0.020 m² K/W |

ENVIRONMENTAL SPECIFICATIONS

|    |                                                                                        |
|----|----------------------------------------------------------------------------------------|
| CE |  CE |
|----|----------------------------------------------------------------------------------------|

LAYING DIRECTION

LEOXX reserves the right to make technical adjustments that lead to quality improvement.