



PURLINE 1500 PEA022 | SILVER GREY
| EXTERNAL CORNER

PRODUCT SPECIFICATIONS

Surface structure	Soft structure	
Number of tufts	ISO 1763	o p/m²
Total weight	EN ISO 24340 (EN 429) 	3450 g/m²
Total thickness	EN ISO 24346 (EN 428) 	2.5 mm
Composition	Heterogeneous with ecuran as the main component; a high-performance composite material made primarily from vegetable oils such as rapeseed or castor oil and naturally occurring mineral components such as chalk.	
Manufacturation process	Calender process	
Design	Gemêleerd	

PERFORMANCE SPECIFICATIONS

Dimensional stability	EN ISO 23999	 ≤ 0.15%
Residual indentation	EN ISO 24343-1	 ≤ 0.10 mm
Slip resistance	EN 13893 DIN 51130	 R9
Antistatic	EN 1815	 Permanent antistatisch
Light fastness	DIN EN ISO 105 B02	 ≥ 7
Usage classification	EN ISO 10874 EN 685	 34  43
Castor chair test (Type W)	EN ISO 4918 (EN 425)	 Geschikt voor bureaustoelen met zachte zwenkwielen
Light Reflectance Value (LRV - Y)		 29.7

TECHNICAL SPECIFICATIONS

Static electrical propensity	EN 1815		≤ 2.0 kV
Flammability	DIN EN 13501		Cfl-s1
Thermal resistance	ISO 8302		ca. 0.01 m² K/W
Impact sound insulation	ISO 10140		4 dB

ENVIRONMENTAL SPECIFICATIONS

Formaldehyde emissions	EN 717-1		Complies with European E1 standard (European chamber method EN 717-1)
The Blue Angel			Ja
Phthalate free			Yes
VOC emissions		  	A+ émissions dans l'air intérieur Floorscore M1
CO ₂ neutral			Ja
Recyclable			Ja
CE			CE

PRODUCT OPTIONS

XXtra Care



We like to keep our floors beautiful for as long as possible. With XXtra Care we offer everyone with a LEOXX floor a periodical maintenance concept, matching the floor and its function. Ask about the possibilities and extend the lifespan of your floor.

LAYING DIRECTION

LEOXX reserves the right to make technical adjustments that lead to quality improvement.

LEOXX B.V.

Sasdijk 14, 8281 BM Genemuiden (NL)

T +31 30 635 10 00 | E info@leoxx.com | I www.leoxx.com

IBAN NL87 RABO 0305 9745 13 | KvK 30151348 | BTW NL807305157B01



[View product](#)