



PURLINE 1500 PLR384C |  
CHOCOLATE BROWN | BROADLOOM  
200 CM

PRODUCT SPECIFICATIONS

|                         |                       |                                                                                                                                                                                                                    |           |
|-------------------------|-----------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------|
| Surface structure       |                       | Soft structure                                                                                                                                                                                                     |           |
| Number of tufts         | ISO 1763              | o p/m²                                                                                                                                                                                                             |           |
| Total weight            | EN ISO 24340 (EN 429) |                                                                                                                                                                                                                    | 3400 g/m² |
| Total thickness         | EN ISO 24346 (EN 428) |                                                                                                                                                                                                                    | 2.5 mm    |
| Composition             |                       | Heterogeneous with ecuran as the main component; a high-performance composite material made primarily from vegetable oils such as rapeseed or castor oil and naturally occurring mineral components such as chalk. |           |
| Manufacturation process |                       | Calender process                                                                                                                                                                                                   |           |
| Design                  |                       | Gemêleerd                                                                                                                                                                                                          |           |

PERFORMANCE SPECIFICATIONS

|                            |                      |  |                                                    |
|----------------------------|----------------------|--|----------------------------------------------------|
| Dimensional stability      | EN ISO 23999         |  | ≤ 0.15%                                            |
| Residual indentation       | EN ISO 24343-1       |  | ≤ 0.10 mm                                          |
| Slip resistance            | EN 13893 DIN 51130   |  | R9                                                 |
| Usage on stairs            |                      |  | Suitable for stairs                                |
| Antistatic                 | EN 1815              |  | Permanent antistatisch                             |
| Light fastness             | DIN EN ISO 105 B02   |  | ≥ 7                                                |
| Usage classification       | EN ISO 10874 EN 685  |  | 34                                                 |
|                            |                      |  | 43                                                 |
| Castor chair test (Type W) | EN ISO 4918 (EN 425) |  | Geschikt voor bureaustoelen met zachte zwenkwielen |

Light Reflectance Value (LRV - Y)



17.9

## TECHNICAL SPECIFICATIONS

Static electrical propensity

EN 1815



≤ 2.0 kV

Flammability

DIN EN 13501



Cfl-s1

Thermal resistance

ISO 8302



ca. 0.01 m² K/W

Impact sound insulation

ISO 10140



4 dB

## ENVIRONMENTAL SPECIFICATIONS

Formaldehyde emissions

EN 717-1



Complies with European E1 standard (European chamber method EN 717-1)

The Blue Angel



Ja

Phthalate free

Yes

VOC emissions



A+ émissions dans l'air intérieur



Floorscore



M1

CO<sub>2</sub> neutral

Ja

Recyclable



Ja

CE



CE

## PRODUCT OPTIONS

XXtra Care



We like to keep our floors beautiful for as long as possible. With XXtra Care we offer everyone with a LEOXX floor a periodical maintenance concept, matching the floor and its function. Ask about the possibilities and extend the lifespan of your floor.

## LAYING DIRECTION

LEOXX reserves the right to make technical adjustments that lead to quality improvement.

## LEOXX B.V.

Sasdijk 14, 8281 BM Genemuiden (NL)

T +31 30 635 10 00 | E info@leoxx.com | I www.leoxx.com

IBAN NL87 RABO 0305 9745 13 | KvK 30151348 | BTW NL807305157B01



[View product](#)