



PURLINE 1500 PS378 | SPRINGTIME
ORANGE | WELDING RODS

PRODUCT SPECIFICATIONS

Total thickness	EN ISO 24346 (EN 428)		4.0 mm
Composition			PE
Manufacturation process			Calender process
Design			Uni

PERFORMANCE SPECIFICATIONS

Dimensional stability	EN ISO 23999		≤ 0.15%
Residual indentation	EN ISO 24343-1		≤ 0.10 mm
Slip resistance	EN 13893 DIN 51130		R9
Antistatic	EN 1815		Permanent antistatisch
Light fastness	DIN EN ISO 105 B02		≥ 7
Usage classification	EN ISO 10874 EN 685		34
			43
Castor chair test (Type W)	EN ISO 4918 (EN 425)		Geschikt voor bureaustoelen met zachte zwenkwielen
Light Reflectance Value (LRV - Y)			54.4

TECHNICAL SPECIFICATIONS

Static electrical propensity	EN 1815		≤ 2.0 kV
Flammability	DIN EN 13501		Cfl-s1

Thermal resistance	ISO 8302		ca. 0.01 m ² K/W
--------------------	----------	---	-----------------------------

ENVIRONMENTAL SPECIFICATIONS

Formaldehyde emissions	EN 717-1		Complies with European E1 standard (European chamber method EN 717-1)
------------------------	----------	---	---

The Blue Angel		Ja
----------------	---	----

Phthalate free		Yes
----------------	--	-----

VOC emissions		A+ émissions dans l'air intérieur
		FloorScore
		M1

CO ₂ neutral		Ja
-------------------------	---	----

Recyclable		Ja
------------	---	----

CE		CE
----	---	----

PRODUCT OPTIONS

XXtra Care



We like to keep our floors beautiful for as long as possible. With XXtra Care we offer everyone with a LEOXX floor a periodical maintenance concept, matching the floor and its function. Ask about the possibilities and extend the lifespan of your floor.

LAYING DIRECTION

LEOXX reserves the right to make technical adjustments that lead to quality improvement.

LEOXX B.V.

Sasdijk 14, 8281 BM Genemuiden (NL)

T +31 30 635 10 00 | E info@leoxx.com | I www.leoxx.com

IBAN NL87 RABO 0305 9745 13 | KvK 30151348 | BTW NL807305157B01



[View product](#)